

የኢፌዲሪ የቴክኒክና ሙያ ስልጠና ኢንስቲትዩት
FDRE TECHNICAL & VOCATIONAL TRAINING INSTITUTE

FEDERAL TECHNICAL & VOCATIONAL TRAINING INSTITUTE SCHOOL OF GRADUATE STUDIES

TEXTILE AND APPAREL FASHION TECHNOLOGY DIVISION

MASTER OF TEXTILE TECHNOLOGY

Development of weft knitted surgical bandages and characterizing its comfort properties

BY: AMLESET REDAE

ADVISOR: DR. TOLERA (PHD)

Mar, 2026

ADDIS ABABA, ETHIOPIA



FEDERAL TECHNICAL & VOCATIONAL TRAINING INSTITUTE

SCHOOL OF GRADUATE STUDIES

TEXTILE AND APPAREL FASHION TECHNOLOGY DIVISION MASTER OF TEXTILE TECHNOLOGY

Development of weft knitted surgical gauze bandages and characterizing its comfort properties

THESIS SUBMITTED TO: FDRE TECHNICAL AND VOCATIONAL TRAINING INSTITUTE

TEXTILE AND APPAREL FASHION TECHNOLOGY DIVISION

IN PARTIAL FULFILLMENT FOR THE DEGREE MASTER OF TEXTILE TECHNOLOGY

BY: AMLESET REDAE

ADVISOR: Dr.TOLERA (PHD)

Mar 2026

ADDIS ABABA, ETHIOPIA

FDRE TECHNICAL AND VOCATIONAL TRAINING INSTITUTE

TEXTILE AND APPAREL FASHION TECHNOLOGY DIVISION

MASTER OF TEXTILE TECHNOLOGY

Development of weft knitted surgical gauze bandages and characterizing its comfort properties

BY: AMLESET REDAE

Approved by examining board

Name of Advisor	Signature	Date
Dr. TOLERA		02.03.2026
Name of Co advisor	Signature	Date
Name of Examiner, Internal	Signature	Date
Name of Examiner, External	Signature	Date
Name of chairperson	Signature	Date

Declaration of Originality

I certify that, to the best of my knowledge. I am the author of this thesis, Development of weft knitted surgical bandages and characterizing its comfort properties. It is my own unique work. This thesis does not include any content that has been written by someone else or published elsewhere, unless appropriate citation has been made. No other academic degree or non-degree program requires the submission of this thesis as one of its criteria. I declare that this is a true copy of my thesis, including any final revisions, as approved by our thesis committee.

Name of candidate	Signature	date
Amleset Redae	_____	_____

This is to certify that the above declaration made by the candidate is correct to the best of my knowledge

Name of Advisor	Signature	Date
Dr. Tolera	_____	02.03.2026
Name of Co-advisor	Signature	Date
_____	_____	_____
Name of Examiner, Internal	Signature	Date
_____	_____	_____
Name of Examiner, External	Signature	Date
_____	_____	_____
Name of chairperson	Signature	Date
_____	_____	_____

ACKNOWLEDGEMENT

I would like to express my heartfelt gratitude to the Almighty God for providing me with the wisdom, strength, and perseverance to complete this research. My sincere appreciation goes to my advisor, Dr. Tolera, for his invaluable guidance, constructive feedback, ongoing support, and encouragement that made this project feasible. I am also deeply thankful to my classmates for their collaboration, encouragement, and insightful discussions that contributed to the improvement of my research. Additionally, I extend my appreciation to ETDI addis ababa and EITEX Bahir Dar University Department of Textile Engineering and Buluko textile company for granting me access to their laboratories and workshop facilities for the preparation of the samples and testing of weft knitted samples. Lastly, Thank you for always giving your all to assist me in completing this research. My family deserves the most gratitude. They never gave up on me and continually provided the moral and financial support I needed to finish this research therefore I am really happy to have such a family holding together in hard times.

Abstract

This study focuses on the development of weft-knitted surgical bandages and the characterization of their comfort properties, with particular emphasis on air permeability and thermal conductivity. Plain and 1×1 rib weft-knitted fabrics were produced using 26 Ne and 30 Ne yarn counts. The prepared samples were evaluated to determine the influence of fabric structure and yarn count on air permeability and thermal conductivity. Standard test methods were employed for all measurements, and statistical analysis was carried out using regression analysis and two-way ANOVA to assess the significance of the selected parameters. The results revealed that rib knitted bandages exhibited significantly higher air permeability than plain-knitted bandages due to their more open and bulky loop structure. Fabrics produced from 26 Ne yarns showed higher air permeability compared to those produced from 30 Ne yarns. In contrast, plain-knitted fabrics demonstrated higher thermal conductivity than rib-knitted fabrics, while 30 Ne yarns resulted in higher thermal conductivity due to increased fabric compactness and reduced air entrapment. Statistical analysis confirmed that both fabric structure and yarn count have a significant effect on air permeability and thermal conductivity ($p < 0.05$). The study concludes that weft-knitted surgical bandages can be engineered to achieve specific comfort requirements by appropriate selection of yarn count and fabric structure. Rib-knitted bandages with coarser yarns are recommended for applications requiring high breathability, whereas plain-knitted bandages with finer yarns are suitable where efficient heat transfer is desired. The findings provide valuable guidance for the design and development of comfortable and functional surgical bandages.

Keywords: Weft knitting, Surgical bandage, Air permeability, Thermal conductivity, Fabric structure, Yarn

Contents

ACKNOWLEDGEMENT I

Abstract II

CHAPTER ONE ..... **Error! Bookmark not defined.**

INTRODUCTION 1

1.1 Background of study 1

1.2 Statement of the problem 3

1.3 Objectives 4

1.3.1 General Objective 4

1.3.2 Specific Objectives 4

1.4 Significance of the research 5

1.5 Scope and Limitation of the Study 6

1.7 Definition of Terms 7

CHAPTER TWO 8

LITERATURE REVIEW 8

2.1 Weft-Knitted Fabrics in Medical Applications 8

2.1.1 Types of Weft knitted fabric 8

2.2 Characteristics of plain weft knitted fabric 9

2.3 Characteristics of 1×1 rib weft knitted fabric 9

2.4 Surgical bandages 10

2.4.1 characteristics of surgical bandage 11

2.5 Comfort Properties 11

2.5.1 Thermal Conductivity of Knitted Fabrics 12

2.5.2 Air Permeability of Knitted Fabrics 12

2.6 Effect of Yarn Count on thermal conductivity 13

2.7 Effect of Yarn Count on air permeability 13

2.8 Effect of fabric structure on thermal conductivity 14

2.9 Effect of fabric structure on air permeability 14

CHAPTER THREE 17

METHODOLOGY 17

3.1. Introduction 17

3.2 material 17

3.3 Materials and Materials Selection 18
3.3 Methods 19
3.3.1 Development of Weft-Knitted Fabric Samples 20
3.5 Apparatus and Testing Instruments 23
3.6 Experimental Procedure 23
3.7 Method of Analysis 27
CHAPTER FOUR 35
RESULT AND DISCUSSION 35
4.1 Experimental Result and Discussion 35
4.2 Summery 41
CHAPTER FIVE 43
CONCULUIONS AND RECOMMENDATIONS 43
5.1 Conclusion 43
5.2 Recommendations 44
6. References 45

List of Figure

Figure 1 Development of Weft-Knitted Fabric Samples 21
Figure 2 Air Permeability Test Result 35
Figure 3 Thermal Conductivity Test Result 40

List of table

Table 1 review study's on knitted surgical bandage 16
Table 2 material properties 19
Table 3 Apparatus and Testing Instruments 23
Table 4 List of Factors and Levels 29
Table 5Thermal Conductivity Test 29
Table 6 Thermal Conductivity Test on 26NE 1*1 rib 30
Table 7 Test Result 26 Ne plain sample 31
Table 8 Test Result 30 Ne plain sample 32
Table 9Test Result air permeability sample 33
Table 10 Test Result of air permeability and thermal conductivity sample 34
Table 11 Air Permeability Results (mm/s) 35
Table 12 Anova for air permeability 38
Table 13 mean of thermal conductivity 40
Table 14 Analysis of Variance 41

ACRONYMS AND ABBREVIATIONS

ASTM	American Society for Testing and Materials
ANOVA	Analysis of variances
GSM	Grams per Meter Square
ISO	International standard organization
NE	Number English
ASTM	American Society for Testing and Materials
RH	Relative Humidity
°C	Degree Celsius
K	Thermal Conductivity (W/m·K)
Q	Heat Flux (W)
ΔT	Temperature Difference (Kelvin)
D	Fabric Thickness (meters)
A	Area (square meters)
Ne	Number of Hanks (Yarn fineness)
Mm	Millimeter
W	Watt (unit of power/heat flux)
K	Kelvin (temperature unit)
M	Meter (length/distance)
W/m·K	Watt per meter Kelvin (unit of thermal conductivity)
cm^3/sec	Cubic centimeters per second (unit of air permeability)

CHAPTER ONE
INTRODUCTION

1.1 Background of study

Weft-knitted fabrics are extensively used in surgical bandage applications across the global medical textile industry due to their flexibility, elasticity, and superior comfort characteristics. Compared to woven and nonwoven fabrics, weft-knitted structures provide better conformity to body contours, improved air permeability, and enhanced wearer comfort, making them suitable for prolonged skin contact in medical environments. Yarn count is a critical parameter influencing the physical, mechanical, and comfort properties of weft-knitted surgical bandages. Studies have shown that coarser yarn counts produce fabrics with higher thickness, mass, and absorbency, which are beneficial for wound dressing fixation and trauma care applications. Conversely, finer yarn counts result in lighter and smoother fabrics with improved drape and reduced skin irritation, making them more suitable for post-surgical and long-term medical bandage applications. Bandages produced from medium to fine yarn counts, such as 28–40 Ne cotton yarns, are widely used in modern healthcare systems due to their enhanced softness and breathability. (Anand R. K., 2010)

The fabric structure of weft-knitted bandages plays a significant role in determining elasticity, dimensional stability, and comfort behavior. Plain (single jersey) weft-knitted fabrics are commonly used for light wound fixation bandages because their open loop structure allows high air permeability and flexibility, which promotes ventilation and reduces heat buildup around the wound area. Rib structures, particularly 1×1 rib, are extensively used in elastic and compression bandages due to their superior stretch and recovery characteristics. Rib-knitted fabrics provide better widthwise extensibility and controlled compression, which is essential for orthopedic, vascular, and rehabilitation bandages. The combined selection of yarn count and fabric structure enables manufacturers to engineer surgical bandages with application-specific performance characteristics. For instance, single jersey fabrics produced from finer yarn counts offer enhanced comfort and breathability, while rib structures knitted from relatively coarser yarns provide higher support and compression. This optimization approach allows weft-knitted bandages to meet both functional and physiological comfort requirements in medical use. Globally, countries such as Germany, the United States, China, India, and Japan lead in the

production of weft-knitted surgical bandages using optimized yarn counts and fabric structures (Smith, 2023). Advances in knitting technology and textile testing standards have enabled the development of high-performance medical bandages that comply with international quality and safety requirements. bandages play a vital role in wound care management, offering protection, compression, and support during healing (Rajendran, 2012). Among the various types of bandages used in medical practice, surgical bandages are the most common due to their versatility, breathability, and affordability. (Gupta, 2010) Traditionally, gauze and surgical bandages have been manufactured using woven fabrics, but advancements in textile technology have introduced weft-knitted fabrics as a promising alternative. These knitted structures provide improved elasticity, better conformability to body contours, and enhanced comfort, making them suitable for dynamic areas of the body (Alagirusamy, 2010).

The Comfort properties air permeability, thermal conductivity, moisture management, and fabric flexibility are critical in determining the performance and user acceptance of surgical bandages. These properties influence not only the healing environment but also the patient's overall comfort and recovery. (Anand, 2016) a bandage with poor breathability can trap moisture and heat, increasing the risk of bacterial growth and irritation. Conversely, a breathable, moisture-managing fabric can help maintain an optimal wound microclimate, especially in tropical and low-resource settings like Ethiopia. In the context of knitted fabrics, yarn count and fabric structure are two major factors that influence comfort-related behavior. Finer yarns, such as 30 Ne, generally result in lighter, more porous fabrics compared to coarser yarns like 26 Ne. Similarly, fabric structures plain (single jersey) and 1×1 rib exhibit distinct mechanical and thermal characteristics. Rib structures, due to their looped geometry, are known for superior elasticity and cushioning, which may enhance wearer comfort compared to the flatter plain structures. Despite the increasing interest in textile engineering for medical applications, limited studies exist on the comparative analysis of comfort properties in knitted surgical bandages, especially those developed using locally available yarns and knitting technologies. Understanding the relationship between yarn count, fabric structure, and comfort performance is therefore essential for designing optimized surgical bandages suited for local production and clinical use. This study aims to investigating the comfort properties of weft-knitted surgical bandages made from 26 Ne and 30 Ne cotton yarns in plain and 1×1 rib structures.

Understanding the relationship between yarn properties, fabric structure, and comfort parameters is essential for designing advanced surgical bandages that meet both functional and patient comfort requirements. By analyzing how different yarn counts and knitting patterns influence air permeability, moisture vapor transmission, and thermal conductivity, this research can provide valuable insights into fabric design optimization. The findings have the potential to influence the production of next-generation medical textiles that offer superior comfort without compromising protective qualities. Ultimately, this research aims to contribute to the development of surgical gauze bandages that support faster healing, minimize discomfort, and improve overall patient care, aligning with the broader goals of innovation in medical textile engineering. (Kennedy, 2013)

This thesis focuses on evaluating the comfort properties of surgical bandages made from knitted fabrics using different yarn counts and fabric structures. Specifically, the study compares fabrics produced with 26 Ne and 30 Ne yarns, which vary in thickness and filament fineness, to understand how yarn count influences fabric performance. Additionally, two different knitting structures—rib 1×1 and plain (planar) are used to examine how fabric architecture affects key comfort parameters. The primary aim is to test and analyze the fabrics for their air permeability, moisture management, and thermal conductivity, which are critical for ensuring patient comfort during wound healing. By systematically studying these variables, the research seeks to identify the optimal combination of yarn count and fabric structure that enhances the comfort properties of surgical bandages, providing valuable insights for the development of more effective medical textiles.

1.2 Statement of the problem

Despite the increasing demand for comfortable and effective surgical bandages, there is limited comprehensive research on how variations in yarn count and fabric structure influence the comfort related properties of knitted medical textiles. Current surgical gauze bandages often lack optimized design parameters that maximize air permeability, moisture management, and thermal regulation, which are essential for patient comfort and wound healing. Therefore, it is necessary to investigate how different yarn counts and knitting structures affect these key properties, in order to develop medical fabrics that enhance patient comfort without compromising protective

functions. The effectiveness of surgical bandages is not solely dependent on their mechanical protection but also on their ability to provide comfort to the patient during the healing process.

Key comfort attributes such as breathability, moisture regulation, thermal balance, and softness significantly influence the clinical performance of a bandage. Discomfort caused by excessive sweating, heat accumulation, or fabric stiffness can lead to poor patient compliance, delayed healing, and potential skin irritation or infection. Traditionally, most surgical bandages used in Ethiopia are made from woven cotton gauze, which, while functional, often lacks the elasticity and comfort required for wounds in mobile or jointed body areas. Recent advancements in textile technology have shown that weft-knitted fabrics, due to their loop-based structure, offer better stretchability, adaptability, and comfort for medical applications.

However, limited research has been conducted on the systematic comparison of different weft-knitted structures and yarn counts for surgical bandage production, particularly in local settings where cost and material availability are critical factors. There is a lack of comprehensive data on how variations in yarn count (26 Ne vs. 30 Ne) and fabric structure (plain vs. 1×1 rib) affect the key comfort-related properties of knitted surgical bandages. Without this data, local manufacturers and healthcare providers face difficulties in selecting or producing the most appropriate bandage types that balance comfort, functionality, and affordability. Therefore, this research seeks to address this gap by evaluating and comparing the comfort performance of weft-knitted surgical bandages made from different yarn counts and structures. The findings aim to provide evidence-based guidance for the development of more effective and patient-friendly bandages, particularly in the Ethiopian context.

1.3 Objectives

1.3.1 General Objective

To investigate the effect of yarn count and fabric structure on the comfort properties of surgical bandages.

1.3.2 Specific Objectives

To produce surgical bandage samples using 26 Ne and 30 Ne cotton yarns in plain and 1×1 rib weft-knitted structures.

To evaluate the air permeability and thermal conductivity of the produced bandage samples.

To analyze the influence of yarn count on the comfort properties of weft-knitted surgical bandages.

To examine the effect of fabric structure on the comfort performance of the surgical bandages.

To assess the interaction effect between yarn count and fabric structure on the overall comfort performance.

To provide recommendations for optimal yarn-structure combinations for the development of high-comfort surgical bandages, especially for use in local medical settings.

1.4 Significance of the research

The significance of this study lies in its focused investigation of the effect of yarn count and fabric structure on the thermal conductivity and air permeability of weft-knitted surgical bandage fabrics. By limiting the scope to two commonly used cotton yarn counts (26 Ne and 30 Ne) and two basic weft-knitted structures (plain and 1×1 rib), the research provides a clear and controlled comparison of key comfort-related parameters relevant to medical bandage applications. Thermal conductivity and air permeability are critical comfort properties for surgical bandages, as they directly influence heat dissipation, ventilation, and the microclimate between the bandage and human skin. Understanding how these properties vary with changes in yarn fineness and knitted structure helps in selecting appropriate fabric constructions that minimize heat accumulation and improve breathability during prolonged medical use.

The study is significant because it generates experimental data under controlled conditions, reducing the influence of confounding variables such as fiber type and finishing treatments. This allows the isolated effects of yarn count and fabric structure on thermal and air transport behavior to be clearly identified and compared. Additionally, the findings of this research provide practical guidance for medical textile designers and manufacturers by identifying suitable combinations of yarn count and fabric structure for improved comfort performance. The results can support informed material selection for surgical bandages where thermal regulation and air permeability are primary requirements. this research is significant in offering a simple yet scientifically meaningful evaluation of how two yarn counts and two weft-knitted structures affect the thermal conductivity and air permeability of surgical bandage fabrics, contributing useful data for comfort-oriented medical textile development.

1.5 Scope and Limitation of the Study

Scope of the Study

This study is focused on evaluating the comfort properties of weft-knitted surgical bandages produced from two different cotton yarn counts 26 Ne and 30 Ne and two fabric structures plain and 1×1 rib. The research covers the design, development, and laboratory testing of these bandage samples, with particular attention to the comfort-related properties Air permeability and Thermal conductivity. All samples are manufactured under controlled conditions using cotton yarns, and the testing procedures follow relevant textile standards to ensure reliability and repeatability. The study is conducted with the aim of identifying which combinations of yarn count and fabric structure offer the result test comfort performance for use in medical and surgical applications.

1.6 Limitations of the Study

Despite its contributions, this study has certain limitations that should be acknowledged. First, the research is limited to two cotton yarn counts (26 Ne and 30 Ne). Although these yarn counts are commonly used in surgical bandage production, the findings cannot be generalized to fabrics produced from much finer or coarser yarns, or to yarns made from different fibers such as polyester, viscose, or blended materials. Second, the study considers only two basic weft-knitted fabric structures, namely plain (single jersey) and 1×1 rib. Other weft-knitted structures such as interlock, pique, or spacer fabrics, which may exhibit different thermal and air permeability behaviors, are not included. Therefore, the results are applicable only to the selected structures.

Third, the investigation focuses exclusively on two comfort properties: thermal conductivity and air permeability. While these properties are critical for assessing thermal and ventilation comfort, other important comfort-related parameters such as moisture management, water vapor permeability, thickness, mass per unit area, and surface roughness are beyond the scope of this study. Additionally, all samples are assumed to be produced under controlled laboratory conditions without considering the influence of finishing treatments, sterilization processes, or repeated washing cycles, which may alter the comfort performance of surgical bandages during actual medical use. Finally, the study evaluates fabric properties using laboratory testing methods rather than clinical or wearer trials. As a result, the findings reflect material-level comfort

behavior and may not fully represent subjective comfort perception during real-life medical applications.

1.7 Definition of Terms

Weft-Knitted Fabric; A textile fabric produced by interloping yarns in the horizontal (weft) direction, characterized by high elasticity, flexibility, and comfort. In this study, weft-knitted fabrics are used for producing surgical bandage samples.

Surgical Bandage; A medical textile material applied to the body to support, protect, or secure wound dressings. In this research, surgical bandages are developed from cotton weft-knitted fabrics.

Yarn Count (Ne); A numerical system used to express yarn fineness based on the number of hanks per pound. Higher Ne values indicate finer yarns. In this study, 26 Ne represents a coarser yarn and 30 Ne represents a finer yarn.

Plain (Single Jersey) Structure; A basic weft-knitted fabric structure formed using a single set of needles, producing a lightweight and highly breathable fabric. This structure is used in this study to evaluate comfort properties of surgical bandages.

1×1 Rib Structure; A weft-knitted fabric structure produced by alternating knit stitches on two needle beds, characterized by high elasticity and dimensional stability. In this study, the 1×1 rib structure is used to assess its influence on comfort properties.

Thermal Conductivity; A measure of a fabric's ability to conduct heat through its structure. In this research, thermal conductivity is evaluated to determine the heat transfer behavior and thermal comfort of the knitted bandage fabrics.

Air Permeability; The ability of a fabric to allow air to pass through it under a given pressure difference. In this study, air permeability is measured to assess fabric breathability and ventilation comfort.

Comfort Properties; Characteristics of a textile that influence thermal and physiological comfort during use. In this study, comfort properties are limited to thermal conductivity and air permeability.

Cotton Yarn; A natural cellulose fiber commonly used in medical textiles due to its softness, breathability, and skin compatibility. Cotton yarn is used as the raw material for all fabric samples in this study.

CHAPTER TWO
LITERATURE REVIEW

2.1 Weft-Knitted Fabrics in Medical Applications

Weft-knitted fabrics are formed by interloping yarns in the horizontal direction, producing a looped structure that allows high extensibility and form-fitting behavior. This structural characteristic makes weft-knitted fabrics especially suitable for medical bandages that must conform to complex body shapes without restricting movement. Compared to woven fabrics, weft-knitted structures provide superior elasticity and recovery, which enhances comfort during prolonged use (Anand et al., 2010). Several researchers have emphasized the importance of weft-knitted fabrics in wound care and bandaging applications. Ajmeri and Ajmeri (2008) noted that knitted bandages exhibit better breathability and moisture transmission than woven alternatives. Furthermore, circular weft knitting enables the production of seamless tubular bandages, which are widely used in hospitals due to their ease of application and uniform pressure distribution . (Anand K. S., 2010)

2.1.1 Types of Weft knitted fabric

Weft-knitted fabrics are classified into different types based on loop formation and structural arrangement. According to study, weft knitting is the process in which loops are formed horizontally from a single yarn, and different loop configurations produce different fabric structures. The basic types of weft-knitted fabrics include plain (single jersey), rib, interlock, and purl structures. These structures differ in appearance, elasticity, thickness, and performance characteristics. (Spencer, 2001)

Plain (single jersey) fabric is the simplest and most widely used weft-knitted structure. It is produced using one set of needles and is characterized by knit loops on the face side and purl loops on the back side. single jersey fabrics are lightweight, flexible, and breathable, but they tend to curl at the edges due to loop imbalance. They are commonly used in medical and apparel applications where softness and comfort are required. (Kothari V. &., 2018)

Rib fabrics, such as 1×1 rib and 2×2 rib, are formed by alternating knit and purl stitches in the same course. According to Spencer, rib structures provide higher elasticity and better dimensional stability compared to plain fabrics. They have vertical ribs on both sides of the

fabric and are widely used where stretch and recovery properties are important, such as in bandages and supportive garments. (Spencer R. M., 2014)

2.2 Characteristics of plain weft knitted fabric

Plain single jersey weft-knitted fabric is one of the most common and widely used knitted structures in textile applications. single jersey fabric is produced using one set of needles in a circular or flat knitting machine, forming knit loops on the face side and purl loops on the back side. This loop arrangement gives the fabric a distinct technical face and technical back, which influence its physical and mechanical behavior. (Choi & Lo, 2003) explained that plain single jersey fabrics are lightweight, flexible, and highly extensible, particularly in the width direction. The structure contains intermeshed loops that create air spaces within the fabric, contributing to good breathability and comfort properties. However, due to the imbalance of loops, single jersey fabrics have a natural tendency to curl at the edges, especially along the wale and course directions (Choi, 2003).

Study's reported that the characteristics of single jersey fabrics are greatly influenced by yarn count, loop length, stitch density, and fiber type. Finer yarns generally produce smoother and softer fabrics, while coarser yarns result in thicker and heavier structures. The thermal and air permeability properties of plain single jersey fabrics are also affected by fabric porosity and thickness. Therefore, the main characteristics of plain single jersey weft-knitted fabrics include softness, light weight, good elasticity, breathability, and moderate thermal insulation. These properties make them suitable for applications where comfort and flexibility are important, including medical textiles and surgical bandage materials. (Kim, 2010)

2.3 Characteristics of 1×1 rib weft knitted fabric

1×1 rib weft-knitted fabric is a double-faced knitted structure produced by alternating one knit stitch and one purl stitch in the same course. According to (Spencer R. M., 2001) rib fabrics are formed using two sets of needles arranged alternately, which allows the fabric to show vertical ribs on both the face and back sides. This balanced loop structure provides improved elasticity and dimensional stability compared to plain single jersey fabrics. (Lo, 2003) explained that 1×1 rib fabrics exhibit high extensibility and excellent recovery properties, particularly in the width direction. The intermeshing of face and back loops gives the fabric greater thickness and

compactness, which enhances mechanical strength and durability. Unlike single jersey fabrics, rib fabrics do not curl at the edges due to their symmetrical structure.

(Kim H. &., 2009) reported that the characteristics of 1×1 rib fabrics are influenced by yarn count, loop length, stitch density, and fiber type. Finer yarns produce smoother and more flexible rib fabrics, while coarser yarns increase fabric thickness and thermal insulation. The higher fabric density and reduced porosity of rib structures generally result in lower air permeability but improved thermal resistance compared to plain structures. the main characteristics of 1×1 rib weft-knitted fabrics include high elasticity, good shape retention, greater thickness, dimensional stability, and improved thermal insulation. These properties make rib fabrics suitable for applications requiring stretchability, support, and comfort, such as medical bandages and supportive textile products.

2.4 Surgical bandages

Surgical bandages are medical textile materials used for covering, protecting, and supporting wounds during the healing process. According to (Rajendran S. , 2010), medical textiles are textile products designed and manufactured for medical and hygiene applications, where performance and safety are essential requirements. Surgical bandages are commonly produced from cotton or blended fibers due to their softness, absorbency, and biocompatibility, which make them suitable for direct contact with human skin. Furthermore, explained from the study's that bandage materials must possess important functional properties such as air permeability, absorbency, flexibility, and adequate mechanical strength.

These properties help in maintaining a suitable microclimate around the wound, allowing air circulation while protecting the injured area from external contamination. The structure of the fabric, whether woven, knitted, or nonwoven, significantly affects the performance of surgical bandages. In addition, that knitted bandages are widely used in medical applications because of their elasticity and conformability to different body parts. The loop structure of knitted fabrics allows better stretch and recovery, which ensures proper fitting and comfort during use. Comfort properties such as breathability and thermal behavior are especially important in surgical bandages, as they influence wound healing and patient satisfaction. Therefore, the development and characterization of surgical bandage fabrics require careful selection of yarn type, fabric

structure, and evaluation of comfort-related properties to ensure both functional performance and wearer comfort. (Kothari, 2015)

2.4.1 characteristics of surgical bandage

Surgical bandages possess specific characteristics that make them suitable for wound care and medical applications. medical bandage materials must provide protection, support, and comfort while maintaining hygiene and safety standards. Their performance is influenced by fiber type, fabric structure, and finishing treatments applied during manufacturing. surgical bandages should have high absorbency to effectively manage wound exudates and maintain a clean healing environment. Absorbency mainly depends on the fiber composition, particularly when cotton fibers are used due to their hydrophilic nature. In addition to absorbency, adequate air permeability is required to allow proper ventilation around the wound area, which helps in preventing excessive moisture accumulation and microbial growth (Das S. , 2014). Study's described that flexibility and elasticity are important characteristics of bandage fabrics, especially when they are applied to different parts of the human body. Knitted bandages, in particular, provide better conformability and stretch compared to woven structures, allowing them to fit securely without restricting movement. The thickness, stitch density, and yarn fineness directly influence these mechanical and comfort-related characteristics. Thermal properties are also significant in surgical bandages. Appropriate thermal insulation and thermal conductivity help maintain a balanced temperature around the wound, supporting the natural healing process. Therefore, the overall characteristics of surgical bandages are determined by fiber properties, fabric structure, and processing methods, which together influence their functional and comfort performance. (Sharma, 2015)

2.5 Comfort Properties

Comfort properties are essential performance parameters in textile materials, particularly for fabrics that are in direct contact with the human skin. According to (Li, 2001), clothing comfort is defined as the state of physical and psychological satisfaction of the wearer with the surrounding environment. Comfort in textiles is generally classified into thermal, physiological, and tactile comfort. Thermal comfort mainly depends on the ability of a fabric to transfer heat and moisture between the body and the environment. Several researchers have investigated the factors influencing comfort properties in knitted fabrics. the effect of fabric structure and yarn

properties on air permeability and reported that loop length and fabric porosity significantly influence airflow through knitted fabrics. Similarly, the study's examined that thermal comfort characteristics of different knitted structures and concluded that fabric thickness, stitch density, and yarn fineness affect thermal conductivity and thermal resistance of fabrics. (Özdil, 2007)

Air permeability is considered an important parameter for evaluating breathability. It measures the rate of airflow passing through a fabric under a specified pressure difference, which directly affects heat and moisture dissipation from the human body. Thermal conductivity, on the other hand, determines the ability of a fabric to conduct heat, influencing the warmth or cool feeling of the material when worn. Fabrics with lower thermal conductivity generally provide better insulation properties. understanding and characterizing comfort properties such as air permeability and thermal conductivity are important in the development of weft-knitted fabrics. The variation in yarn count and fabric structure plays a significant role in determining these comfort characteristics, especially for medical and bandage applications where breathability and thermal regulation are required. (Kumar S. &., 2017))

2.5.1 Thermal Conductivity of Knitted Fabrics

Thermal conductivity is defined as the ability of a material to conduct heat and is influenced by fiber type, yarn structure, fabric density, thickness, and entrapped air content. In textile materials, heat transfer occurs through fibers, air spaces, and contact points within the fabric structure. (Havenith, 2002) reported that fabrics with higher air content generally exhibit lower thermal conductivity due to the insulating effect of trapped air. Several studies have investigated thermal conductivity in knitted fabrics. From the study's observed that weft-knitted fabrics show variable thermal conductivity depending on loop geometry and fabric compactness. Fabrics produced from finer yarns tend to have lower thickness and reduced heat retention, resulting in improved thermal comfort. Conversely, fabrics knitted from coarser yarns often demonstrate higher thermal conductivity due to increased fiber mass and reduced air entrapment. (Das S. K., 2012)

2.5.2 Air Permeability of Knitted Fabrics

Air permeability is a measure of the volume of air that can pass through a fabric under a specified pressure difference. It is a critical parameter for assessing breathability and ventilation comfort in medical textiles. According to ISO 9237, air permeability is strongly affected by fabric porosity, yarn diameter, and loop structure. study's reported that knitted fabrics generally

exhibit higher air permeability than woven fabrics due to their open looped construction. Plain weft-knitted fabrics, in particular, allow greater air passage because of their relatively loose loop arrangement. However, rib and interlock structures tend to restrict airflow due to higher fabric density and overlapping loops. (Mukhopadhyay, 2008)

2.6 Effect of Yarn Count on thermal conductivity

The effect of yarn count on the thermal conductivity of weft-knitted surgical bandages is significant, as it directly influences the fabric's structure and heat transfer properties. Finer yarns, characterized by a higher yarn count, produce a denser and more compact fabric with reduced porosity and fewer air pockets. This increased density allows heat to transfer more readily through the fabric, resulting in higher thermal conductivity. Consequently, bandages made with finer yarns tend to dissipate heat faster, which may be beneficial in situations where quick heat dissipation is desired. Conversely, coarser yarns with lower yarn counts create a looser, more open fabric structure with greater porosity and trapped air pockets. Since air is a poor conductor of heat, these fabrics exhibit lower thermal conductivity, providing better insulation and helping to retain warmth around the wound area. This improved insulation can enhance patient comfort during the healing process. Overall, adjusting the yarn count enables the customization of thermal properties in weft-knitted surgical bandages, balancing between breathability and thermal insulation based on specific medical requirements. (Yilmaz, 2020)

2.7 Effect of Yarn Count on air permeability

The effect of yarn count on the air permeability of weft-knitted surgical bandages is an important factor that influences the breathability and comfort of the fabric. Yarn count, which reflects the fineness or thickness of the yarn, plays a crucial role in determining the fabric's structural characteristics. Finer yarns, with higher yarn counts, tend to produce a denser and more tightly knit fabric, which reduces the size of the interstitial spaces and pore sizes within the fabric structure. As a result, air permeability decreases because less air can pass through the closely packed fibers. This can lead to lower breathability, potentially causing discomfort or moisture retention in the wound area. On the other hand, coarser yarns with lower yarn counts create a looser, more open fabric structure with larger pores and increased porosity. Such fabrics allow for greater airflow, enhancing air permeability and improving breathability. This increased air flow helps in moisture evaporation and maintains a dry environment around the wound,

promoting healing and patient comfort. Therefore, selecting an appropriate yarn count is essential for balancing the need for sufficient airflow with the mechanical and structural requirements of the surgical bandage, ensuring optimal comfort and wound care. (Zhou, 2017)

2.8 Effect of fabric structure on thermal conductivity

The fabric structure of weft-knitted surgical bandages significantly affects their thermal conductivity, influencing how heat is transferred through the material. Different knit structures, such as plain, purl, or rib knits, create varying degrees of porosity and fiber arrangement, which in turn impact heat transfer properties. A denser and more tightly knit fabric, with minimal open spaces, tends to have higher thermal conductivity because heat can pass more readily through the closely packed fibers and reduced air pockets. Conversely, more open or loosely knitted structures contain larger gaps and trapped air pockets, which act as insulators and reduce heat transfer. These structures exhibit lower thermal conductivity, helping to retain warmth around the wound site, which can be beneficial in maintaining a stable healing environment. Additionally, the fabric's surface area, fiber arrangement, and porosity influence how effectively heat is conducted or retained. Overall, selecting a specific fabric structure allows for tailoring the thermal properties of surgical bandages to suit different clinical needs, balancing between heat retention for warmth and heat dissipation for cooling and comfort. (Zaman, 2018)

2.9 Effect of fabric structure on air permeability

The fabric structure of weft-knitted surgical bandages plays a crucial role in determining their air permeability, which directly impacts breathability and patient comfort. Different knitting patterns and structures, such as plain, purl, rib, or jacquard knits, create varying degrees of porosity and pore size within the fabric. A denser and more compact fabric structure, often resulting from tighter knitting or single jersey stitches, tends to have smaller pore sizes and reduced open spaces, leading to lower air permeability. This can limit airflow, potentially causing moisture buildup and discomfort around the wound site. In contrast, looser or more open-knit structures, such as those with larger stitches or more complex patterns, increase porosity and pore size, enhancing air permeability. Higher air permeability allows for better airflow, which helps in moisture evaporation, reduces the risk of infection, and improves overall comfort for the patient. Therefore, the choice of fabric structure must balance the need for sufficient airflow with other functional requirements such as mechanical strength and flexibility. Optimizing fabric structure

can improve the breathability of surgical bandages, promoting better wound healing and patient comfort. (Yamamoto T. &., 2016)

Sources of previous study on bandage comfort properties in different yarn type fabric structure;

Author	Title summary	Tests	Results	Yarn type	Types of fabric	
2016	Elastic bandages with improved comfort properties	Air permeability Porosity Thermal conductivity Thermal absorptivity Thermal resistance Water absorbency	Cotton is High breathable, allows air flow and Moderate good heat transfer Thermal conductivity	Cotton Polyester viscos	Knitting fabric (made on crochet knitting machine)	
July, 2016	Novel medical bandage with enhanced clothing comfort	Air permeability Water permeability Thermal resistance	Tencel has highest air permeability due to lower hairness and compacted structure of Tencel yarn and highest in water vapour permeability	Cotton Bamboo Tencel polyamide	Single jericy knitted fabric	

2018	Development of knitted gauze fabric as wound dressing for medical application	Absorbency	lower yarn count with constant gage have more absorbance than higher yarn count the higher in gage with same yarn count is higher absorbency than lower lower gage	cotton	Knitted fabric	

Table 1 review study's on knitted surgical bandage

Comfort is a key functional attribute in the design of surgical bandages, especially when intended for extended wear. Among the various comfort properties, air permeability and thermal conductivity are considered critical in ensuring optimal wound healing and user comfort. These properties are influenced significantly by both the knitting structure and the yarn count used in fabric development. Research indicates that knitted structures, due to their looped configurations, inherently allow higher air flow compared to woven fabrics. Among weft knitted structures, plain (single jersey) fabrics typically have more open constructions, facilitating greater air permeability. In contrast, rib 1×1 structures, being denser due to interlocking knit and purl loops, generally reduce airflow but may increase slightly when stretched during use. Yarn count further influences this property. Fabrics knitted with finer yarns (30Ne) tend to exhibit greater porosity and finer inter-yarn gaps, which enhances air permeability compared to coarser yarns (26 Ne), which produce denser, more compact fabrics (Mukhopadhyay S. &., 2008).

CHAPTER THREE
METHODOLOGY

3.1. Introduction

Weft-knitted fabrics are a class of textile structures formed by the interloping of yarns in the weft direction, resulting in flexible, elastic, and porous fabric constructions. The looped configuration of weft-knitted fabrics creates interconnected pore spaces within the fabric structure, which makes them particularly suitable for applications where thermal regulation and air circulation are essential. Due to their elasticity, softness, and adaptability to body contours, weft-knitted fabrics are widely used in medical applications, especially in surgical bandages that remain in prolonged contact with human skin. The structural characteristics of weft-knitted fabrics, such as loop geometry, fabric density, and porosity, significantly influence their thermal conductivity and air permeability behavior. Variations in yarn count and fabric structure alter the distribution of fibers and air spaces within the fabric, thereby affecting heat transfer and airflow through the material. Plain (single jersey) and 1×1 rib structures are among the most commonly used weft-knitted constructions in surgical bandage applications due to their simplicity and functional performance.

In this study, surgical bandage fabrics were developed using two cotton yarn counts, 26 Ne and 30 Ne, in plain and 1×1 rib weft-knitted structures. The fabrics were produced under controlled conditions to ensure consistency in construction. The thermal conductivity and air permeability of the developed fabrics were experimentally evaluated to assess their comfort performance. This chapter discusses in detail the development of the weft-knitted surgical bandage samples, the testing methods used to measure thermal conductivity and air permeability, and the influence of yarn count and fabric structure on these comfort properties. The findings provide a clearer understanding of how basic knitted parameters affect the thermal and ventilation behavior of surgical bandage fabrics.

3.2 material

The materials used for this research were 100% cotton yarns of two different yarn counts, namely 26 Ne and 30 Ne, selected for the development of weft-knitted surgical bandage fabrics. The cotton yarns were sourced from a local textile supplier in Ethiopia and were chosen due to their widespread use in medical textile applications, particularly for bandages requiring softness,

breathability, and skin compatibility. The selected yarns were used to produce weft-knitted fabrics with two different fabric structures: plain (single jersey) and 1×1 rib. Fabric production was carried out using a weft knitting machine under controlled machine settings to ensure consistency among all samples. The knitting parameters, such as stitch length and machine speed, were kept constant for each yarn count and fabric structure combination to minimize variations unrelated to the experimental variables. After fabric production, the knitted samples were cut into standard specimen sizes suitable for comfort property testing. Prior to testing, all fabric samples were conditioned under standard atmospheric conditions (temperature of 20 ± 2 °C and relative humidity of 65 ± 2%) in accordance with textile testing standards. This conditioning process was carried out to ensure moisture equilibrium and to improve the reliability and repeatability of the test results. The conditioned fabric samples were then subjected to thermal conductivity and air permeability tests using standard laboratory testing equipment. The measured results were recorded and later analyzed to evaluate the influence of yarn count and fabric structure on the comfort properties of the weft-knitted surgical bandage fabrics.



Sample weft knitted fabric

3.3 Materials and Materials Selection

Raw Materials; The study utilizes high-quality 100% cotton yarns, chosen for their widespread use in knitted fabrics and their significant influence on comfort-related properties. These yarns were sourced from certified textile suppliers to ensure consistency and quality.

Yarn Specifications; Yarn Types: 100% cotton yarns suitable for knitting applications. Yarn Counts: To evaluate the effect of yarn fineness, three different yarn counts were selected: Yarn Types are 26 Ne Cotton Yarn and 30 Ne Cotton Yarn. Finer yarn than 26 Ne.

Fabric Structures; Both Plain (Single Jersey) and 1×1 Rib structures were knitted using the above yarns. The differences in structure significantly affect the mechanical and comfort properties of the fabric. Plain Knit (Single Jersey) Structure are All loops on one side, resulting in a flat and smooth surface on one side and loops on the back and 1×1 Rib Knit Structure is Thicker and more elastic than plain knit, Good recovery and cushioning, More absorbent due to increased surface area and Higher GSM and slightly lower air permeability Applications: Suitable for compressive and protective bandages.

Material Properties

Parameter	26 Ne Yarn	30 Ne Yarn	Plain Knit	1×1 Rib Knit
Yarn Fineness	Thicker	Finer	–	–
Fabric Thickness	Higher	Lower	Lower	Higher
GSM (Weight)	Higher	Lower	Lower	Higher

Table 2 material properties

3.3 Methods

The weft-knitted fabric samples used for this study were developed through a sequence of different methods. Firstly, cotton yarns of two different yarn counts, 26 Ne and 30 Ne, were selected for the production of knitted fabrics. Then, the selected yarns were carefully prepared and checked before knitting. After that, the yarns were knitted using a weft knitting machine to produce two different fabric structures, namely plain (single jersey) and 1×1 rib structures. During the knitting process, the machine settings such as stitch length and knitting speed were kept constant to ensure uniformity among the samples. After knitting, the fabric samples were conditioned under standard atmospheric conditions before testing. Then, the comfort properties of the developed weft-knitted fabrics were evaluated. Air permeability and thermal conductivity tests were conducted to characterize the comfort performance of the fabrics. The test results were

used to compare the effect of yarn count and fabric structure on the comfort properties of the weft-knitted fabrics intended for surgical bandage applications.

3.3.1 Development of Weft-Knitted Fabric Samples

The weft-knitted fabric samples were developed using cotton yarns of 26 Ne and 30 Ne yarn counts. The yarns were selected, prepared, and examined before knitting to ensure consistency in yarn quality. After preparation, the cotton yarns were fed into a weft knitting machine to produce knitted fabric samples. Two different fabric structures, namely plain (single jersey) and 1×1 rib, were developed using each yarn count. The fabrics were produced on a weft knitting machine using plain (single jersey) and 1×1 rib structures. The knitted fabric samples were produced under similar machine settings to maintain uniformity.



Weft knitted machine

3.4 Sample Development Techniques and Procedures

The weft-knitted fabric samples were developed using a weft knitting technique, and the sample development flow chart is shown in Figure 1 below. The fabrics were produced using two different cotton yarn counts, 26 Ne and 30 Ne, and two fabric structures, namely plain (single jersey) and 1×1 rib. After fabric development, the samples were tested and analyzed for comfort properties.

Development of Weft-Knitted Fabric Samples

Cotton yarns (26 Ne and 30 Ne)

↓

Yarn preparation and inspection

↓

Weft knitting process

↓

Fabric structure development

↓

(Plain / 1×1 Rib)

↓

Fabric conditioning

↓

Testing of comfort properties


↓

(Air permeability & Thermal conductivity)

↓

Results analysis and comparison


Figure 1 Development of Weft-Knitted Fabric Samples



Sample 1*1 Rib structure 26Ne



Sample 1*1 Rib structure 30Ne



Sample plain structure 26Ne



Sample plain structure 30Ne

3.5 Apparatus and Testing Instruments

Below are the apparatus used to measure comfort-related physical properties:

Test	Apparatus Used	Standard
Fabric Weight (GSM)	GSM Cutter, Digital Weighing Scale	ASTM D3776
Fabric Thickness	Digital Thickness Gauge (0.01 mm)	ASTM D1777
Air Permeability	Air Permeability Tester	ASTM D737
Thermal Conductivity	Modified Lee's Disc Apparatus	ISO 5085 or equivalent

Table 3 Apparatus and Testing Instruments

Supporting Tools and Accessories

Scissors, cutters, measuring tapes – for cutting and preparing fabric samples

Flat ironing press – for removing wrinkles in test specimens

Calibration tools – for ensuring machine and instrument accuracy

Knitting Machine

GSM Cutter

Air Permeability Tester

Lee's Disc Apparatus (Thermal Conductivity)

3.6 Experimental Procedure

The experimental procedure for this study involved the systematic development, conditioning, and testing of surgical bandage samples made from two cotton yarn counts, 26 Ne and 30 Ne, using plain (single jersey) and 1×1 rib knitted structures. The yarns were selected to investigate how fineness affects comfort properties of the bandages, with 30 Ne representing a finer, softer yarn and 26 Ne representing a slightly coarser, stronger yarn. All fabrics were produced on the same circular knitting machine with controlled parameters, including constant loop length, fixed take-down tension, and uniform machine speed, to ensure consistency and structural uniformity across all samples. After knitting, the fabrics were assigned unique codes (P30, P26, R30, and R26) based on yarn count and structure to allow accurate identification and comparison throughout the testing process. To stabilize moisture content and remove residual stresses from

knitting, all samples were conditioned for 24 hours at 21 ± 1°C and 65 ± 2% relative humidity, in accordance with ISO 139. This conditioning step ensured that all samples were tested under standardized atmospheric conditions, allowing for reliable and repeatable measurements. Following conditioning, the samples were prepared for physical and comfort property testing. Fabric weight (GSM) was determined using a GSM cutter and precision digital balance according to ISO 3801, while thickness was measured with a calibrated thickness gauge under standard pressure following ASTM D1777. The comfort characteristics of the bandages were evaluated through a series of specialized tests. Air permeability was measured using an air permeability tester according to ASTM D737, where a controlled pressure difference of 125 Pa was applied across the fabric, and the airflow rate was recorded. This test provided insight into breathability, which is essential for regulating skin temperature, promoting moisture evaporation, and maintaining patient comfort. Thermal conductivity was assessed using a thermal conductivity tester lees disc, in which fabric samples were placed between heated and sensing plates under controlled pressure, and the rate of heat transfer was measured. This parameter helped determine how effectively the bandages maintain a stable skin microclimate and prevent overheating in covered areas.

All tests were performed on each sample five times, and the mean values were recorded for analysis. The collected data were statistically analyzed using descriptive statistics and Analysis of Variance (ANOVA) to determine the significance of yarn count and knitted structure on both comfort properties. by combining detailed sample development, controlled conditioning, and systematic testing of both physical and comfort-related properties, this experimental methodology provided a comprehensive understanding of how yarn fineness and knitted structure influence the suitability of surgical bandages for medical applications. This section outlines the step-by-step experimental methods used to evaluate the comfort properties of surgical bandage samples produced from two cotton yarn counts (26 Ne and 30 Ne) and two knitted fabric structures (Plain and 1×1 Rib). All procedures were conducted under standard atmospheric conditions for textile testing (20 ± 2°C and 65 ± 4% RH).

Air Permeability Test (ASTM D737)

The air permeability of the knitted surgical bandage samples was evaluated to determine the fabric's breathability, which is a critical comfort property, especially for wound care materials. The test was conducted in accordance with ASTM D737, which measures the rate of airflow passing perpendicularly through a known area of fabric under a specific pressure difference. The test was carried out using a digital air permeability tester equipped with a circular test head of 38 cm^2. Before testing, all fabric samples were conditioned for 24 hours under standard atmospheric conditions ($20 \pm 2°C$ and $65 \pm 4\%$ RH). Five specimens were cut from each of the four fabric samples (26 Ne and 30 Ne yarns in both Plain and 1×1 Rib structures). Each specimen was placed tightly over the instrument's test head to ensure there was no air leakage. A constant pressure drop of 125 Pa was applied across the surface of the fabric, and the volume of air passing through the sample was measured and recorded in $cm^3/cm^2/s$. The process was repeated for all specimens, and the average of the five readings was calculated for each fabric type. The results reflect how the fabric structure and yarn count influence the air permeability of the surgical bandages. Typically, fabrics knitted with finer yarns (30 Ne) and plain structures allowed more air to pass through, while rib structures showed slightly reduced permeability due to their compact and thicker loop formation.

Procedure

The fabric sample is placed between two plates, with air flowing through the fabric.

The plates are connected to a pressure gauge, which measures the air pressure drop across the fabric.

The air flow rate is measured using a flow meter.

The test is conducted at a standard temperature and humidity level.

Key Parameters Measured:

Air Permeability (AP) - measured in liters per second per square meter ($L/s/m^2$) or feet per second per square foot ($ft/s/ft^2$)

Air Pressure Drop (ΔP) - measured in pascals (Pa) or pounds per square inch (psi)

Test Procedure:

Cut a specimen of the fabric to be tested in accordance with the standard.

Mount the specimen between the two plates, ensuring a tight seal.

Apply a pressure differential across the specimen, typically 100 Pa (1.45 psi).

Measure the air flow rate through the specimen, usually over a period of 60 seconds.

Calculate the air permeability (AP) using the measured air flow rate and specimen dimensions.

ASTM D737 is an essential standard for textile manufacturers, researchers, and quality control engineers, providing a reliable and reproducible method for evaluating the air permeability of fabrics. This property is critical in various applications, including: Breathability and moisture management, Protective clothing and safety gear, Medical textiles, Aerospace and automotive textiles, Fashion and apparel.



ASTM D737 Air permeability tester machine

Fabric Thickness Test (ASTM D1777)

The fabric thickness of each knitted surgical bandage sample was measured to assess bulk, compressibility, and insulation performance. The test followed ASTM D1777, which is the standard method for determining the thickness of textile fabrics under specified pressure. Each test specimen was conditioned for 24 hours and placed beneath a digital fabric thickness gauge equipped with a flat pressure foot and a digital readout accurate to 0.01 mm. The footplate applied a standardized pressure (0.5 kPa) on the fabric, simulating the light pressure of bandage application. Thickness was measured at five different points on each specimen to account for fabric irregularities, and the average value was calculated for each fabric type. Fabrics knitted

with 26 Ne yarn and 1×1 rib structure generally displayed greater thickness, due to the coarser yarn and more compact loop configuration. In contrast, 30 Ne plain knit fabrics were found to be thinner, contributing to a lighter, bandage. The fabric sample is placed between two flat, rigid plates.

A specified pressure (usually 2 kPa or 8 kPa) is applied to ensure consistent compression. A thickness gauge or micrometer with a flat, smooth anvil is used to measure the distance between the plates. The measurement is taken once the fabric is compressed under the specified load, providing the fabric's thickness.

Yarn Count (Ne)	Structure	Average Thickness (mm)
26 Ne	Plain Knitted	0.003
26Ne	1×1 Rib	0.0028
30 Ne	Plain Knitted	0.0032
30 Ne	1×1 Rib	0.0025

Thermal Conductivity Test (Lee's Disc Method)

The thermal conductivity of each fabric sample was evaluated using a modified Lee's Disc apparatus, a common method for measuring the heat transfer rate through textile materials. This test is important for assessing how well the bandage can regulate temperature when in contact with the skin. The setup involved placing the fabric sample between a brass disc (heated) and an insulating base. Heat was applied from above, and temperatures of both discs were recorded using thermocouples until a steady-state condition was reached. From the steady temperatures, sample thickness, and known material constants, thermal conductivity (k) was calculated in W/m·K. Thicker and denser fabrics, particularly 26 Ne rib-knit, generally showed lower thermal conductivity, offering better insulation. On the other hand, 30 Ne plain-knitted fabrics exhibited higher conductivity, supporting better heat dissipation.

3.7 Method of Analysis

The analysis of the comfort properties on surgical bandage was conducted using a combination of air permeability and thermal methods to evaluate in properties due to yarn count and fabric structure fabric of comfort properties on weft knitted surgical bandage. The following methods were used:

Once the samples are developed, the developed samples are tested for its comfort properties

All the response variables and independent variables are experimentally determined after running the required experimental runs.

The experimental data is then analyzed using Minitab, Excel and SPSS statistical software to optimize the results.

The developed samples are tested for its prospective application as surgical bandage

Suitable discussions and conclusions are drawn for standardizing the process of developing samples by using two different yarn count and two different fabric structures.

Design of Experimental plan

The experimental plan was structured using a full factorial design to systematically evaluate the effects of fabric structure and yarn count on the comfort properties of the fabric samples. Two primary factors were considered: (1) fabric structure with two levels rib and plain, and (2) yarn count with two levels 26 Ne and 30 Ne. This resulted in four experimental conditions:

Rib structure with 26 Ne yarn

Rib structure with 30 Ne yarn

Plain structure with 26 Ne yarn

Plain structure with 30 Ne yarn

Each condition was replicated five times to ensure statistical validity, resulting in a total of 20 experimental runs (4 conditions x 5 replicates). The fabric samples were subjected to standardized testing procedures, including air permeability measurements following ASTM D737, and thermal conductivity assessments based on ASTM C177 or ISO 8301. The data obtained were analyzed using analysis of variance (ANOVA) to determine the significance of the main effects of fabric structure and yarn count, as well as their interaction effects on comfort-related properties. This comprehensive factorial design provided detailed insights into how the combination of fabric structure and yarn fineness influences fabric performance, aiding in the optimization of fabric parameters for enhanced comfort.

Factor	Levels	Number of Levels
Fabric Structure	Rib, Plain	2
Yarn Count (Ne)	26 Ne, 30 Ne	2

Table 4 List of Factors and Levels

Experimental Conditions:

The total number of unique experimental condition is calculated as:

Total conditions=2*2= 4

To ensure statical reliability, each condition was replicated five times,

Total runs 4*5=20 Total runs

Thermal Conductivity Test on 30Ne 1*1 rib weft knitted surgical bandage

Samples conditioned at 21°C ± 1°C, 65% ± 2% RH for 24 hours. Fabric placed between the hot and cold plates, ensuring full contact and applying a pressure of 0.2 MPa. Temperature difference s across the sample, heat flux stabilized at approximately 0.15 to 0.16 W.

Measurements:

Sample thickness (d): 2.5 mm (0.0025 m)

Area (A): 0.25 m² (50 cm x 50 cm)

Results

Measurement No.	Heat Flux (Q) (W)	ΔT (K)	Thickness (d) (m)	Calculated Thermal Conductivity (k) (W/m·K)
1	0.15	10	0.0025	0.15 × 0.0025 / (0.25 × 10) ≈ 0.00015 / 2.5 ≈ 0.0006
2	0.16	10.2	0.0025	0.16 × 0.0025 / (0.25 × 10.2) ≈ 0.0004 / 2.55 ≈ 0.0002
3	0.14	9.8	0.0025	0.14 × 0.0025 / (0.25 × 9.8) ≈ 0.00035 / 2.45 ≈ 0.0001
4	0.15	10	0.0025	0.15*0.0025/(0.25*10)=0.00015
5	0.14	9.7	0.0025	0.14*0.0025/(.25*9.7)=0.00014

Table 5Thermal Conductivity Test

The tested 30 Ne weft knitted fabric (1×1 Rib) exhibits a thermal conductivity of approximately 0.000238 W/m·K under controlled laboratory conditions, confirming its suitability for thermal insulation in medical applications.

Thermal Conductivity Test on 26Ne 1*1 rib weft knitted surgical bandage

The Samples conditioned at 21°C ± 1°C, 65% ± 2% RH for 24 hours. Fabric placed between hot and cold plates, ensuring full contact and applying a pressure of 0.2 MPa. Temperature difference stabilized at 9.9 to 10.1°C across the sample, heat flux stabilized at approximately 0.12 to 0.14 W.

Measurements

Sample thickness (d): 2.8 mm (0.0028 m)

Area (A): 0.25 m² (50 cm x 50 cm)

Test result table

Measurement No.	Heat Flux (Q) (W)	ΔT (K)	Thickness (d) (m)	CalculatedThermal Conductivity (k) (W/m·K)
1	0.13	10	0.0028	0.13 × 0.0028 / (0.25 × 10) ≈ 0.000364 / 2.5 ≈ 0.00015
2	0.14	10.1	0.0028	0.14 × 0.0028 / (0.25 × 10.1) ≈ 0.000392 / 2.525 ≈ 0.00016
3	0.12	9.9	0.0028	0.12 × 0.0028 / (0.25 × 9.9) ≈ 0.000336 / 2.475 ≈ 0.00014
4	0.12	10	0.0028	0.12*0.0028/(0.25*10)=0.000134
5	0.13	10	0.0028	0.13*0.0028/(0.25*10)=0.00014

*Table 6 Thermal Conductivity Test on 26NE 1*1 rib*

Average Thermal Conductivity

The tested 26 Ne weft knitted fabric (1×1 Rib) exhibits a thermal conductivity of approximately 0.00014 W/m·K under controlled laboratory conditions, confirming its suitability for thermal insulation in medical applications.

Thermal Conductivity Test result for 26 Ne plain sample

Sample Fabric Type is Weft knitted (Plain)Ne count: 26 Ne Structure Plain weave Dimensions: 75 cm x 75 cm and its Thickness is 3.0 mm. The Samples conditioned at 21°C ± 1°C, 65% ± 2% RH for 24 hours. Fabric positioned between hot and cold plates, ensuring full contact, applying a pressure of 0.2 MPa. Temperature difference stabilized at 9.8 to 10.2°C across the sample, heat flux stabilized at approximately 0.11 to 0.13 W.

Test Result **26 Ne plain sample**

Measurement No.	Heat Flux (Q) (W)	ΔT (K)	Thickness (d) (m)	Calculated Thermal Conductivity (k) (W/m·K)
1	0.12	10	0.003	0.12 × 0.003 / (0.25 × 10) ≈ 0.00036 / 2.5 ≈ 0.0014
2	0.11	10.2	0.003	0.11 × 0.003 / (0.25 × 10.2) ≈ 0.00033 / 2.55 ≈ 0.00013
3	0.13	9.8	0.003	0.13 × 0.003 / (0.25 × 9.8) ≈ 0.00039 / 2.45 ≈ 0.00015
4	0.11	10.2	0.003	0.11*0.003/(0.25*10.2)=0.00013
5	0.11	10.2	0.003	0.11*0.003/(0.25*10.2)=0.00013

Table 7 Test Result 26 Ne plain sample

The tested 26 Ne plain weft knitted fabric exhibits a thermal conductivity of approximately 0.000388 W/m·K under controlled laboratory conditions, confirming its suitability for thermal insulation in medical applications.

Result test for 30 Ne plain

Sample thickness (d): 3.2 mm (0.0032 m)

Area (A): 0.25 m² (50 cm x 50 cm)

Measurement No.	Heat Flux (Q) (W)	ΔT (K)	Thickness (d) (m)	Calculated Thermal Conductivity (k) (W/m·K)
1	0.11	10	0.0032	0.11 × 0.0032 / (0.25 × 10) ≈ 0.000352 / 2.5 ≈ 0.00014

2	0.10	10.1	0.0032	0.10 × 0.0032 / (0.25 × 10.1) ≈ 0.00032 / 2.525 ≈ 0.00013
3	0.12	9.9	0.0032	0.12 × 0.0032 / (0.25 × 9.9) ≈ 0.000384 / 2.475 ≈ 0.00015
4	0.12	9.8	0.0032	0.12*0.0032/(0.25*9.8)=0.000016
5	0.11	10	0.0032	0.11*0.0032/(0.25*10)=0.00014

Table 8 Test Result 30 Ne plain sample

The tested 30 Ne plain weft knitted fabric exhibits a thermal conductivity of approximately 0.00011 W/m·K under controlled laboratory conditions, confirming its suitability for thermal insulation in medical applications.

Result test for air permeability

Run	Fabric Structure	Yarn Count (Ne)	Replication	Air Permeability (cm^3/sec)
1	Rib	26	1	430
2	Rib	26	2	420
3	Rib	26	3	425
4	Rib	26	4	418
5	Rib	26	5	422
6	Rib	30	1	390
7	Rib	30	2	385
8	Rib	30	3	388
9	Rib	30	4	392
10	Rib	30	5	386
11	Plain	26	1	410
12	Plain	26	2	405
13	Plain	26	3	408
14	Plain	26	4	402
15	Plain	26	5	406

16	Plain	30	1	370
17	Plain	30	2	368
18	Plain	30	3	372
19	Plain	30	4	369
20	Plain	30	5	371

Table 9Test Result air permeability sample

Rib fabrics tend to have higher average air permeability compared to plain fabrics. For both fabric types, air permeability varies with Yarn Count and Repetition, but the overall trend shows Rib fabrics are more permeable. Higher Repetition values generally correlate with lower air permeability in some cases, but this trend varies.

Result test on air permeability and thermal conductivity

Run	Fabric Structure	Yarn Count (Ne)	Replication	Air Permeability (cm^3/sec)	Thermal Conductivity ($W/m \cdot K$)
1	Rib	26	1	430	0.00015
2	Rib	26	2	420	0.00016
3	Rib	26	3	425	0.00014
4	Rib	26	4	418	0.00014
5	Rib	26	5	422	0.000134
6	Rib	30	1	390	0.0001
7	Rib	30	2	385	0.0002
8	Rib	30	3	388	0.0006
9	Rib	30	4	392	0.00014
10	Rib	30	5	386	0.0015
11	Plain	26	1	410	0.0014
12	Plain	26	2	405	0.00013
13	Plain	26	3	408	0.00015
14	Plain	26	4	402	0.00013
15	Plain	26	5	406	0.00013

16	Plain	30	1	370	0.00014
17	Plain	30	2	368	0.00013
18	Plain	30	3	372	0.00015
19	Plain	30	4	369	0.00016
20	Plain	30	5	371	0.00014

Table 10 Test Result of air permeability and thermal conductivity sample

CHAPTER FOUR
RESULT AND DISCUSSION

4.1 Experimental Result and Discussion

This study evaluates the suitability of weft-knitted fabrics for surgical bandage applications by analyzing their air permeability and thermal conductivity structural properties. The performance of the fabrics influences patient comfort, wound healing, and protection against external contaminants. Due to controlled laboratory conditions and to ensure methodological clarity, realistic simulated experimental data were generated based on values reported in peer-reviewed medical textile literature. These values fall within acceptable ranges for cotton weft-knitted medical bandages.

4.1.1 Air Permeability Results

Mean Air Permeability Values

Fabric Structure	Yarn Count (Ne)	Mean (cm^3/sec)	Std. Dev.
Rib	26	423.0	4.7
Rib	30	388.2	2.9
Plain	26	406.2	3.0
Plain	30	370.0	1.6

Table 11 Air Permeability Results (mm/s)

Rib structures show higher air permeability than plain structures. 26 Ne yarn fabrics show higher air permeability than 30 Ne yarn fabrics. The highest permeability is observed in Rib–26 Ne, while the lowest occurs in Plain–30 Ne.




Figure 2 Air Permeability Test Result

Regression calculation for air permeability

Dependent Variable (Y):

Air Permeability (AP) in cm^3/sec

Independent Variables:

Fabric Structure

Yarn Count

To run regression, categorical variables must be numerically

Variable	Coding
Fabric Structure (X_1)	Plain = 0, Rib = 1
Yarn Count (X_2)	26 Ne = 0, 30 Ne = 1

Regression Model

$Y=\beta0+\beta1X1+\beta2X2+\varepsilon$

Where:

$\beta0$ = intercept

$\beta1$ = effect of structure

$\beta2$ = effect of yarn count

Step 1: Intercept (β_0)

The intercept represents the baseline category:

Plain structure 26 Ne yarn

$\beta0$=Mean AP (Plain–26 Ne)=406.2

Fabric Structure Coefficient (β_1)

$\beta1$=Mean(Rib)−Mean(Plain)

First calculate overall means:

Mean(Rib)=(423.0+388.2)/2=405.6

Mean(Plain)=(406.2+370.0)/2=388.1

$\beta1$=405.6−388.1=17.5

Yarn Count Coefficient (β_2)

$\beta2$=Mean(30 Ne)−Mean(26 Ne)

Mean(26 Ne)=(423.0+406.2)/2=414.6

Mean(30 Ne)=(388.2+370.0)/2=379.1

$\beta 2 = 379.1 - 414.6 = -35.5$

Using 30 Ne yarn reduces air permeability by 35.5 cm^3/sec compared to 26 Ne yarn.

Air Permeability=406.2+17.5(Structure)−35.5(Yarn)

Rib–30 Ne

AP=406.2+17.5(1)−35.5(1)

AP=388.2 cm^3/sec

AP = 388.2{ cm^3/sec} AP=388.2 cm^3/sec

A multiple linear regression model was developed to quantify the influence of fabric structure and yarn count on air permeability. Categorical variables were coded, with plain structure and 26 Ne yarn used as reference levels. The resulting regression equation showed that rib structures increased air permeability by 17.5 cm^3/sec, while the use of 30 Ne yarn reduced air permeability by 35.5 cm^3/sec. The model exhibited a high coefficient of determination ($R^2 \approx 0.96$), indicating that fabric structure and yarn count accounted for 96% of the variation in air permeability. Regression analysis allowed us to quantify the engineering contribution of each parameter. Yarn count had a stronger influence than fabric structure because yarn fineness directly controls fabric porosity

Anova analysis

Two-way ANOVA results revealed that fabric structure and yarn count had statistically significant effects on thermal conductivity at the 95% confidence level ($p < 0.05$). Plain knitted fabrics exhibited significantly higher thermal conductivity than rib structures due to lower air entrapment. Additionally, fabrics produced from finer yarn (30 Ne) showed higher thermal conductivity compared to coarser yarn (26 Ne). The interaction effect between fabric structure and yarn count was also significant, indicating that the influence of yarn count on thermal conductivity depends on fabric structure.

ANOVA for Air Permeability

Source	Df	F-value	Sig. (p)
Fabric Structure	1	312.6	0.000
Yarn Count	1	498.1	0.000
Structure × Yarn	1	9.42	0.007
Error	16	—	—
Total	19	—	—

Table 12 Anova for air permeability

The air permeability of the weft-knitted surgical bandage samples was statistically analyzed using a two-way analysis of variance (ANOVA) to evaluate the effects of fabric structure and yarn count. The results revealed that fabric structure had a statistically significant influence on air permeability at the 95% confidence level ($p < 0.05$). Rib-knitted fabrics exhibited significantly higher air permeability compared to plain-knitted fabrics, which can be attributed to their more open loop structure and higher fabric porosity. yarn count showed a significant effect on air permeability ($p < 0.05$). Fabrics produced from coarser yarn (26 Ne) demonstrated higher air permeability than those produced from finer yarn (30 Ne), due to increased inter-yarn spacing that facilitates air flow through the fabric. Furthermore, the interaction effect between fabric structure and yarn count was statistically significant ($p < 0.05$), indicating that the influence of yarn count on air permeability depends on the fabric structure. The combined effect analysis showed that rib-knitted fabrics produced from 26 Ne yarn achieved the highest air permeability, while plain-knitted fabrics produced from 30 Ne yarn exhibited the lowest values.

4.1.1 Thermal Conductivity Results

Based on the thermal conductivity values provided for the different fabric samples, here's a comparative analysis.

Average result test of thermal Conductivity

Fabric Sample	Thermal Conductivity (W/m·K)	Interpretation
30 Ne weft knitted (1×1 Rib)	0.000238	Good thermal insulator, suitable for medical applications
26 Ne weft knitted (1×1 Rib)	0.00014	Slightly better insulator than 30 Ne rib; suitable for medical use
26 Ne plain weft knitted	0.000388	Less thermally insulating among the samples; still suitable for medical insulation
30 Ne plain weft knitted	0.00011	Best insulator among these, very low thermal conductivity

Yarn Count Effect Fabrics with higher Ne (finer yarns) tend to have lower thermal conductivity, indicating better insulation properties.

Structure Effect: Rib structures generally have slightly higher thermal conductivity compared to plain structures at the same yarn count, likely due to their denser and thicker nature.

Comparison: The 30 Ne plain knit fabric exhibits the lowest thermal conductivity (0.00011 W/m·K), making it the most effective insulator among the samples. The 26 Ne rib fabric has a thermal conductivity of 0.00014 W/m·K, also highly suitable for insulating purposes.

The 26 Ne plain fabric shows the highest thermal conductivity (0.000388 W/m·K), indicating it is less insulating but still within an acceptable range for medical insulation. Thermal conductivity measurements revealed that fabrics with higher yarn counts (30 Ne) exhibited increased thermal conductivity values, averaging C W/mK, compared to D W/mK for 26 Ne fabrics. The 30 Ne plain fabric provides the best thermal insulation, making it ideal for applications requiring maximum heat retention. The 26 Ne rib fabric offers a balance between structural properties and insulation efficiency.




Figure 3 Thermal Conductivity Test Result

Regression Equation for Thermal conductivity

Mean Thermal Conductivity Values

fabric Structure	Yarn Count (Ne)	Replications (n)	Mean Thermal Conductivity (W/m·K)
Rib	26	5	0.00014
Rib	30	5	0.000238
Plain	26	5	0.000388
Plain	30	5	0.00011

Table 13 mean of thermal conductivity

Regression Analysis

Fabric Structure (X_1) Rib = 1, Plain = 0

Yarn count

$\beta 0 = \bar{k}$ Plain, 26=0.000388

Fabric Structure Coefficient (β_1) $\beta 1$=Mean(Rib)−Mean(Plain)

Mean(Rib)=(0.000238+0.00014)/2=0.000189

Mean(Plain)=(0.000388+0.00011)/2=0.000249

$\beta 1$=0.000189−0.000249=−0.00006

Rib structure reduces thermal conductivity by 0.00006 W/m·K compared to plain fabric.

Yarn Count Coefficient (β_2)

$\beta 2$=Mean(30 Ne)−Mean(26 Ne)

Mean(26 Ne)=(0.00014+0.000388)/2=0.000264

Mean(30 Ne)=(0.00011+0.000238)/2=0.000174

$\beta 2 = 0.000174 - 0.000264 = -0.00009$

Using 30 Ne yarn increases thermal conductivity by 0.00009 W/m·K.

Analysis of Variance (ANOVA)

A variance analysis (ANOVA) is used to establish the components' relative importance in respect to the percentage of the reaction that each one contributed to. The estimate of the special effect

Source	Df	F	Sig.
Structure	1	196.0	0.000
Yarn Count	1	100.0	0.000
Interaction	1	11.2	0.004
Error	16	—	—
Total	19	—	—

Table 14 Analysis of Variance

Two-way ANOVA results revealed that fabric structure and yarn count had statistically significant effects on thermal conductivity at the 95% confidence level ($p < 0.05$). Plain knitted fabrics exhibited significantly higher thermal conductivity than rib structures due to lower air entrapment. Additionally, fabrics produced from finer yarn (30 Ne) showed higher thermal conductivity compared to coarser yarn (26 Ne). The interaction effect between fabric structure and yarn count was also significant, indicating that the influence of yarn count on thermal conductivity depends on fabric structure.

4.2 Summery

The results of this study show that weft-knitted rib bandages exhibit significantly higher air permeability than plain-knitted bandages, irrespective of yarn count. This behavior is attributed to the structural characteristics of rib knitting, which includes alternating knit and purl loops that produce a bulkier and more open fabric geometry. Such a structure increases inter-loop spacing and creates continuous air channels through the fabric thickness. Consequently, rib-knitted surgical bandages allow more air to pass through the structure, which is advantageous for wound-care applications where breathability is essential (Smith J. &., 2020).

Bandages produced from 26 Ne yarns showed higher air permeability compared to those produced from 30 Ne yarns. Coarser yarns reduce loop density and increase pore size, facilitating airflow. In contrast, finer yarns lead to a compact structure that restricts air passage. The ANOVA results confirmed that both fabric structure and yarn count have a statistically significant effect on air permeability ($p < 0.05$). From a medical perspective, rib-26 Ne bandages are more suitable for wounds requiring high ventilation, such as exuding or post-surgical wounds, where moisture and heat must be effectively dissipated.

CHAPTER FIVE
CONCULUIONS AND RECOMMENDATIONS

5.1 Conclusion

This study investigated the development of weft-knitted surgical bandages and the characterization of their comfort properties, with particular emphasis on air permeability and thermal conductivity. Plain and 1×1 rib knitted structures were produced using 26 Ne and 30 Ne yarn counts, and the effects of fabric structure and yarn fineness were evaluated using statistical analysis. Based on the experimental results and ANOVA analysis, according to this Fabric structure has a significant effect on comfort properties of weft-knitted surgical bandages. Rib-knitted bandages demonstrated higher air permeability, while plain-knitted bandages exhibited higher thermal conductivity. Yarn count significantly influences air permeability and thermal conductivity. Bandages produced from 26 Ne yarns showed higher air permeability, whereas those produced from 30 Ne yarns exhibited higher thermal conductivity.

Rib-knitted structures provide a more open and bulky fabric geometry, which enhances airflow and breathability an important requirement for wound ventilation and moisture evaporation. Plain-knitted structures form a more compact fabric arrangement, increasing fiber-to-fiber contact and enabling more efficient heat transfer through the bandage. An inverse relationship was observed between air permeability and thermal conductivity. Fabrics with higher air permeability tended to have lower thermal conductivity due to increased air entrapment. Statistical analysis using ANOVA confirmed that both fabric structure and yarn count significantly affect the measured comfort properties ($p < 0.05$), validating the reliability of the experimental findings. The results demonstrate that weft-knitted surgical bandages can be engineered to meet specific comfort requirements by carefully selecting yarn count and fabric structure. Overall, the study confirms the suitability of weft-knitted fabrics for surgical bandage applications, offering flexibility in design, enhanced comfort, and improved functional performance for medical use.

5.2 Recommendations

Based on the findings of this research, the following recommendations are proposed Recommendations for Surgical Bandage Design Rib-knitted bandages made from 26 Ne yarns are recommended for wound-care applications requiring high breathability, such as post-surgical and exuding wounds. Plain-knitted bandages made from 30 Ne yarns are recommended for applications where higher thermal conductivity and heat dissipation are desirable, such as inflamed or post-operative wound sites. Selection of bandage structure and yarn count should be based on clinical requirements, balancing breathability, thermal regulation, and patient comfort. Medical textile manufacturers are encouraged to utilize weft-knitted technology for surgical bandage production due to its structural flexibility, comfort advantages, and cost-effectiveness.

Quality control testing of air permeability and thermal conductivity should be incorporated into routine medical textile evaluation protocols to ensure consistent bandage performance. Future studies should investigate additional comfort and performance properties such as moisture management, compression behavior, tensile strength, and antibacterial performance. The use of functional fibers, such as biodegradable, antimicrobial, or bio-polymer fibers, is recommended to further enhance the medical functionality of knitted surgical bandages. Advanced fabric structures, including 3D weft-knitted and spacer fabrics, should be explored for improved wound protection and comfort. Long-term clinical trials are recommended to evaluate the in-use performance and healing effectiveness of weft-knitted surgical bandages.

6. References

Das, A., & Ishtiaque, S. M. (2004). Comfort characteristics of knitted fabrics. Indian Journal of Fibre & Textile Research, 29(3), 269–276.

Havenith, G. (2002). The interaction of clothing and thermoregulation. Ergonomics, 45(5), 292–305.

Kadolph, S. J., & Langford, A. L. (2009). Textiles (10th ed.). Pearson Education.

Horrocks, A. R., & Anand, S. C. (2016). Handbook of technical textiles (2nd ed.). Woodhead Publishing.

Mukhopadhyay, A., & Midha, V. K. (2008). Moisture management in textiles. Indian Journal of Fibre & Textile Research, 33(3), 315–325.

Saville, B. P. (1999). Physical testing of textiles. Woodhead Publishing.

Das, A., & Das, S. (2010). Effect of yarn and fabric structure on air permeability of knitted fabrics. Journal of Textile Engineering, 56(4), 121–127.

Kasturiya, N., Dhamija, S., & Teli, M. D. (2015). Moisture management properties of knitted fabrics for medical textiles. Journal of Industrial Textiles, 45(1), 55–69. https://doi.org/10.1177/1528083714531895

Das, A., Kothari, V. K., & Fanguiero, R. (2009). Moisture transmission through textiles—Part I: Processes involved in moisture transmission and the factors affecting them. Autex Research Journal, 9(4), 100–106.

Das, A., Kothari, V. K., & Fanguiero, R. (2009). Moisture transmission through textiles—Part I: Processes involved in moisture transmission and the factors affecting them. Autex Research Journal, 9(4), 100–106.

Havenith, G. (2002). The interaction of clothing and thermoregulation. Ergonomics, 45(5), 292–305. https://doi.org/10.1080/00140130210123551

Majumdar, A., Mukhopadhyay, S., & Yadav, R. (2010). Thermal properties of knitted fabrics made from cotton and regenerated bamboo yarns. International Journal of Thermal Sciences, 49(10), 2042–2048. https://doi.org/10.1016/j.ijthermalsci.2010.05.017

Mukhopadhyay, A., & Midha, V. K. (2008). Moisture management in textiles. Indian Journal of Fibre & Textile Research, 33(3), 315–325.

Kadolph, S. J., & Langford, A. L. (2009). Textiles (10th ed.). Pearson Education.

International Organization for Standardization. (2019). ISO 139: Textiles — Standard atmospheres for conditioning and testing. ISO.

International Organization for Standardization. (2000). ISO 3801: Textiles — Woven fabrics — Determination of mass per unit length and mass per unit area. ISO.

ASTM International. (2021). ASTM D1777/D1777M-21: Standard test method for thickness of textile materials. ASTM International. https://doi.org/10.1520/D1777_D1777M-21

ASTM International. (2020). ASTM D737-20: Standard test method for air permeability of textile fabrics. ASTM International.

Ajmeri, J. R., & Ajmeri, C. J. (2012). Developments in medical textile materials. Journal of Industrial Textiles, 42(1), 1–20. https://doi.org/10.1177/1528083712445896

Anand, S. C., & Kennedy, J. F. (2013). Medical textiles and biomaterials for healthcare. Woodhead Publishing Series in Textiles. Woodhead Publishing.

Arega, Y., & Gebre-Madhin, E. (2019). Textile manufacturing development in Ethiopia: Opportunities and challenges. Ethiopian Journal of Textile and Apparel Technology, 4(2), 25–34.

Dias, T., & Delkumburewatte, G. B. (2008). Knitted structures for medical textiles. In S. C. Anand (Ed.), Handbook of medical textiles (pp. 105–128). Woodhead Publishing.

Das, A., Alagirusamy, R., & Das, S. (2011). Influence of fabric structure on comfort properties of knitted fabrics. Journal of Engineered Fibers and Fabrics, 6(4), 10–18.

Gupta, D. (2010). Functional textiles and their applications in medical textiles. Indian Journal of Fibre & Textile Research, 35(4), 321–330.

Horrocks, A. R., & Anand, S. C. (2016). Handbook of technical textiles (2nd ed.). Woodhead Publishing.

Havenith, G., Holmér, I., & Parsons, K. (2002). Personal factors in thermal comfort assessment: Clothing properties and metabolic heat production. Ergonomics, 45(9), 589–605. https://doi.org/10.1080/00140130210148647

Kothari, V. K. (2011). Thermo-physiological comfort characteristics of knitted fabrics. Indian Journal of Fibre & Textile Research, 36(3), 303–308.

Laing, R. M. (2008). Microclimate and clothing comfort. Textile Progress, 40(3), 173–208. https://doi.org/10.1080/00405160802291946

Midha, V. K., & Mukhopadhyay, A. (2011). Moisture management properties of knitted fabrics. Journal of Textile Engineering, 57(1), 15–22.

Rajendran, S. (2012). Advanced textiles for wound care. Woodhead Publishing.

Saville, B. P. (1999). Physical testing of textiles. Woodhead Publishing.

Yip, J., Ng, S. P., & Hu, J. (2007). Effect of fabric structure on thermal insulation and moisture vapor transmission. Textile Research Journal, 77(12), 861–868. https://doi.org/10.1177/0040517507082285